

# TEKNOFLOR<sup>®</sup>

HIGH PERFORMANCE FLOORING



NO WAX  
NO BUFF  
EASY TO  
CLEAN

## TIMBERSCAPES<sup>™</sup>

COMMERCIAL RESILIENT SHEET FLOORING



# SATISFACTION. ONE FLOOR AT A TIME.

**TEKNOFLOR® Timberscapes™ Collection.** This durable woodgrained resilient sheet vinyl is the ideal flooring solution for projects that require a rich, warm appearance on a restrictive budget. **Timberscape's** low maintenance surface delivers a flooring system that meets the needs of a variety of industries, features fiberglass reinforcement for excellent dimensional stability and is backed by a powerful 12-year warranty. A great floor that delivers an equally great value. For more information, contact your Teknoflor sales representative.



## DURABLE AND LOW MAINTENANCE

## ENVIRONMENTALLY FRIENDLY

## SAFE

## OVERALL THICKNESS

## WARRANTY

## APPLICATIONS

- **No Wax, No Buff;** easily cleaned by damp mopping or auto-scrubbing
- Embossed surface difficult to scuff or scratch
- Thicker 2.3mm gauge for enhanced performance in heavy traffic areas
- Maintenance savings result in investment payback in approximately two years
- Antimicrobial agent incorporated into the wear layer which effectively inhibits bacterial growth on the flooring surface
- No buff floors mean no bacteria, dust or wax particles are thrown into the air during cleaning
- No odors from floor finishes or strippers; no wax flushed into sewer system
- 52% post-consumer recycled content
- ADA Compliant
- Meets fire test standards and is suitable for use in emergency exits and corridors
- 2.3mm (0.090")
- 12-year commercial warranty
- Ideal for Healthcare, Senior Living, Retail, Corporate/Office, Academic and Hospitality Environments

TIMBERSCAPES™

COMMERCIAL RESILIENT SHEET FLOORING

TEKNOFLOR®





51025 Beech



51024 Poplar



51023 Golden Pecan



51022 Mountain Walnut



53802 Southern Oak



53805 Mountain Oak



53901 Natural Red Oak



51021 Royal Oak



53907 Chestnut Oak




51031 Cherry



51032 Rainier Cherry



53804 Northern Oak



53903 Provincial Oak




53908 Coumarou




53904 Tru Brown Oak



53905 Gunstock Oak



51033 Sable Cherry



53906 Dark Alder

# TEKNOFLOR™ TIMBERSCAPES™

COMMERCIAL RESILIENT SHEET FLOORING

## PRODUCT DATA

STANDARD SPECIFICATION	ASTM F1303
CLASSIFICATION	Type I, Grade 1
BACKING CLASS	Class A 4-Ply fused backing system comprised of PVC Layer, Fiberglass, PVC Internal Layer and Polyester Mesh Back
OVERALL THICKNESS	2.3 mm (0.090")
WEAR LAYER THICKNESS	20 mils (0.020")
PATTERN REPEAT	35.46"W x 24.63"L

## PACKAGING

ROLL SIZE	49.33 Square Yards
DIMENSIONS	5'11" Wide x 75' Long
ROLL WEIGHT	Approximately 275 lbs.
WEIGHT/SY	5.5 lbs.

## PERFORMANCE SPECIFICATIONS

### TEST METHOD

### STANDARD REQUIREMENT

### RESULT

CHEMICAL RESISTANCE	ASTM F925	0 - No Change or 1 - Slight Change	0 - No Change (for standard staining agents)
HEAT STABILITY COLOR CHANGE	ASTM F1514	$\Delta E < 8.0$ avg. @ 7 days	Passes
LIGHT STABILITY COLOR CHANGE	ASTM F1515	$\Delta E < 8.0$ avg. @ 300 hrs.	Passes
SHORT TERM INDENTATION	ASTM F1914	avg. $< 8.0$ avg. @ 50 lbs.	avg. 3.6% 0.003"
STATIC LOAD LIMIT	ASTM F970	250 psi $\leq$ 0.005" Residual Indentation	Exceeds Requirements 750 psi at maximum limit
FLOORSCORE	Certified		SCS-FS-01964
HEAVY METALS	ASTM F963		No Concern with Heavy Metal content
ABRASION RESISTANCE	ASTM D4060	H18 Wheel & 1 kg mass applied	18,000 cycles to see effect on design layer

## SAFETY PERFORMANCE

### TEST METHOD

### STANDARD REQUIREMENT

### RESULT

STATIC COEFFICIENT OF FRICTION (SCOF)	D2047	$\geq 0.5$ SCOF Dry	$\geq 0.6$ SCOF Dry
CRITICAL RADIANT FLUX	E648	Class I: $\geq 0.45$ w/cm <sup>2</sup> Class II: $\geq 0.22$ w/cm <sup>2</sup>	Class I
SMOKE GENERATION	E662	<450 Flaming & Non-Flaming	<450 DM Corrected Flaming & Non-Flaming
SURFACE BURNING CHARACTERISTICS	E84	Class A, B & C	Class B
ANTIMICROBIAL ACTIVITY		Antimicrobial agent incorporated into the wear layer which effectively inhibits bacterial growth on the flooring surface	

APPROVED FOR EMERGENCY EGRESS AREAS - NFPA 101 AND NFPA 99



Schedule  
GS-27F-0504H • GS-27F-0036V  
GS-27F-0015V



TEKNOFLOR™